



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172

परीक्षण प्रमाण पत्र

TEST CERTIFICATE

INTERIM/FINAL REPORT

Number of Copies issued Single

परीक्षण प्रमाण पत्र सं
Test Certificate No

NTH(SR)/EL(C)/2020/0049A-M

जारी होने की तिथि
Date of Issue
29/10/2020कोड नं
Code No
Manualपृष्ठ
Page
1पृष्ठों की संख्या
No of Pages
2जिसे जारी करना है
Issued To

COBA Europe Ltd,

पता
AddressMarlborough Drive, Fleckney, Leicester, LE8 8UR,
United Kingdomग्राहक का सन्दर्भ सं एवं दिनांक
Customer's Ref. No.

By Mail

Date: 13/10/2020

पंजिका सं एवं दिनांक
Register No & Date

0049A-M/NTH(SR)/EL(C)/21/10/2020

परीक्षण सामग्री का विवरण
Description of Test Item

Electrical Insulating matting made of Elastomer, Class - 4

परीक्षण सामग्री का पहचान
Identification of Test Item

Marking :As in the attached sheet "Annexure".

नमूना का विशिष्टि (यदि हों)
Product Specification (If any)

IEC 61111 Edition 2.0 2009-04

नमूना प्राप्ति की तिथि
Date of Receipt of the Test Item

21/10/2020

कार्य सम्पादन की तिथि
Date(s) of Performance of Tests

From: 21/10/2020

To: 29/10/2020

व्यावहृत प्रणाली का पहचान
Method(s) used for Test

Tests as per IEC 61111 Edition 2.0 2009-04

नमूना प्रक्रिया जहाँ प्रासंगिक हों
Sampling Procedure where relevant

Not Applicable

Tested By

A. Muthuraman
SO Electrical

Checked By

Sriilayraj Soundararajan
Scientist- C (Electrical)

Approved By

Sriilayraj Soundararajan
Scientist- C (Electrical)

Notes : 1. The results relate only to the items tested or calibrated

2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

तारमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172

परीक्षण प्रमाण पत्र
TEST CERTIFICATE

INTERIM/FINAL REPORT

Number of Copies issued Single

परीक्षण प्रमाण पत्र सं.

Test Certificate No

NTH(SR)/EL(C)/2020/0049A-M

जारी होने की तिथि

Date of Issue

29/10/2020

कोड नं

Code No

Manual

पृष्ठ

Page

1

पृष्ठों की संख्या

No of Pages

2

Sl. No.

Test Name

Test Result

Limit

1

Test

As in the attached sheet "Annexure"
and the Annexure contains 05 page

As in the attached
sheet "Annexure"

टिप्पणी
Note

- : i).The average ambient conditions of the laboratory during the above tests were as follows:Room temperature, deg C: 28+/-2, Relative humidity, percent: 70 to 75%.
ii).The Oil Resistance test was carried out by transformer oil as requested by the firm.

कैफियत
Remarks

: Comments offered against each test.

Tested By

A.Muthuraman
SO Electrical

Checked By

Sriilayraj Soundararajan
Scientist- C (Electrical)

Approved By

Sriilayraj Soundararajan
Scientist- C (Electrical)

Notes : 1. The results relate only to the items tested or calibrated

2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172

ANNEXURE				
Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH (SR)/EL(C)/2020/0049A-M	29.10.2020	Manual	01	05

1. Description of the sample :

- a. Nomenclature : Electrical Insulating matting made of Elastomer, Class – 4
- b. Colour code : Not Available
- c. Size : 1m x 1.5m, 1m x2.5 m
- d. Quantity : 2 piece
- e. Marking : Not Available

As requested the sample has been subjected to Tests as per IEC 61111 Edition 2.0 2009-04 and the results noted below:-

2. Visual Inspection (Cl. 5.2)

- a. Classification : Class 4
- b. Dimensions : Thickness : 4.8 mm
- c. Workmanship and finish : Satisfactory
- d. Sample Color : Dark Grey

Tested By


A.Muthuraman
S.O(Electrical)

Checked & Approved By


Sriilaraj Soundarrajan
Scientist-C(Electrical)



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

तारमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172


ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH (SR)/EL(C)/2020/0049A-M	29.10.2020	Manual	02	05


3. Tests

Sl.No	Tests	Observed Values	Specified limits
1.	<p>Mechanical Puncture resistance (as per cl. 5.5.2 of the specification)</p> <p>Number of specimens: 2 Size of specimen: 50mm (diameter)</p> <p>Test carried out on both the sides of the matting for two specimens.</p> <p>5mm diameter needle produce a taper with an include angle of 12° and tip rounded to 0.8mm</p> <p>Puncture resistance in N</p> <p>i. Side 1</p> <p>ii. Side 2</p> <p>iii. Average</p>	<p>212</p> <p>200</p> <p>206</p>	Min. 70
2.	<p>Voltage Proof test (as per cl. 5.6.2.2.2 of the specification)</p> <p>Number of specimen: 1</p> <p>A 1270mm x 1270mm sheet of 5mm thick Plexiglass material with picture frame of 762 mm x 762 mm opening the center placed on a grounded metal plate. Mask filled with a conductive material same as thickness to bring the ground electrode at the same level to maintain direct contact with the mat to be tested. (fig:1 of IEC 61111 Edition 2.0 2009-04)</p> <p>An ac voltage of 40kV (rms) at 50 Hz applied and kept constant for 3 minutes.</p>	Withstood the test satisfactorily	Shall withstand test voltage without break down or flashover

Tested By


A.Muthuraman
S.O(Electrical)

Checked & Approved By


Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated

2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH (SR)/EL(C)/2020/0049A-M	29.10.2020	Manual	03	05
Sl.No	Tests	Observed Values	Specified limits	
3.	Voltage Withstand Test (as per cl. 5.6.2.3 of the specification) Number of specimen: 3 Specimen size : 150 x 150 Electrode : 25mm (Top) x 75mm (Bottom) 50 kV ac voltage at 50 Hz applied with a rate of rise of 1000V/sec.	Withstood the test satisfactorily	Shall withstand test voltage without break down or flashover	
4.	Ageing test (as per cl. 5.7 of specification) Number of specimen: 2 Sample conditioned at 70°C for 168 hours. Mechanical Puncture resistance (as per cl. 5.5.2) Test carried out on both the sides of the matting for two specimens. Puncture resistance in N i. Side 1 ii. Side 2	196 194	Min. 164.8 (Minimum 80% of puncture resistance before ageing)	
5.	Flame retardance test (as per cl.5.8.1 of the specification) Number of specimen: 1 Specimen size: 150 x 150mm Application of flame 10s and after withdrawal, the propagation of flame was observed for 55s and it shall not reach any point of 50mm diameter.	Satisfactory No appreciable flame observed	Propagation of flame shall not reached 50 mm diameter of circle	

Tested By

A.Muthuraman
S.O(Electrical)

Checked & Approved By

Sriilayaraj Soundarrajan
Scientist-C(Electrical)



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH (SR)/EL(C)/2020/0049A-M	29.10.2020	Manual	04	05
Sl.No	Tests	Observed Values	Specified limits	
6.	<p>Acid resistance (as per cl. 5.9 of the specification)</p> <p>Number of specimen: 4</p> <p>Size of specimen: 150 x 150mm</p> <p>Sample immersed in Sulfuric acid solution at 23°C±2°C for 8h. Following acid condition, the sample rinsed with water and dried for 2h at 70°C.</p> <p>Mechanical Puncture resistance (as per cl. 5.5.2)</p> <p>Test carried out on both the sides of the matting for two specimens.</p> <p>Puncture resistance in N</p> <p>i. Side 1</p> <p>ii. Side 2</p> <p>Voltage Withstand Test</p> <p>50kV ac voltage at 50 Hz applied with a rate of rise of 1000V/sec.</p>	<p>172</p> <p>176</p> <p>Withstood the test satisfactorily</p>	<p>Min. 154.5</p> <p>(Minimum 75% of puncture before acid resistance)</p> <p>Shall withstand test voltage without breakdown or flashover</p>	
7.	<p>*Oil resistance (as per cl. 5.10 of the specification)</p> <p>Number of specimen: 4</p> <p>Size of specimen: 150 x 150mm</p> <p>Sample conditioned in air at a temperature of 23°C±2°C at 50% RH for 3h. Then the sample is conditioned by immersing in oil at a temperature of 70°C for 24h. Following oil condition, the sample dried using lint free clean cloth.</p> <p>Mechanical Puncture resistance (as per cl. 5.5.2)</p> <p>Test carried out on both the sides of the matting for two specimens.</p> <p>Puncture resistance in N</p> <p>i. Side 1</p> <p>ii. Side 2</p> <p>Voltage Withstand Test: 50kV ac voltage at 50 Hz applied with a rate of rise of 1000V/sec</p>	<p>160</p> <p>158</p> <p>Withstood the test satisfactorily</p>	<p>Min. 154.5</p> <p>(Minimum 75% of puncture without oil conditioning)</p> <p>Shall withstand test voltage without breakdown or flashover</p>	

Tested By

A.Muthuraman
S.O(Electrical)

Checked & Approved By

Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated

2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority



भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)

NATIONAL TEST HOUSE (SR)

तारमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.

Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451172

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH (SR)/EL(C)/2020/0049A-M	29.10.2020	Manual	05	05

Sl.No	Tests	Observed Values	Specified limits
8.	<p>Low Temperature folding test (as per cl. 5.8.2 of the specification)</p> <p>Number of specimen: 3 Size of specimen: 200 x 500mm</p> <p>Sample conditioned at (-)25±3°C for 4 hours. After this the test piece folded at the midpoint and placed between two polyethylene plates and subjected to a force of 100N for 30s.</p> <p>Visual inspection</p> <p>Voltage Withstand Test (An ac voltage at 50 Hz applied with a rate of rise of voltage 1000V/sec. until it reaches 50kV).</p>	<p>Satisfactory</p> <p>No crack or tear break observed</p> <p>Withstood the test satisfactorily</p>	<p>Shall not show crack or tear break observed</p> <p>Shall with stand without breakdown or flashover</p>

Note:

- The average ambient conditions of the laboratory during the above tests were as follows
Room Temperature, in degree C : 28 ± 2°C
Relative Humidity , in percent : 70 to 75%.
- *The Oil Resistance test was carried out by transformer oil as requested by the firm.

Tested By

A.Muthuraman
S.O(Electrical)

Checked & Approved By

Sriilayaraj Soundararajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated

2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority